ALUMINOSILICATE



Aluminosilicate is produced from a naturally occurring mineral, calcined mullite, that is precisely sized as either flour or grain. It is available in three alumina contents: 47%, 60% and 70%. The standard alumina content in the investment casting industry is 47%; which provides a very economical and consistent product. These products are low in iron, alkaline and alkaline earth elements.

In the investment casting industry, the main use of aluminosilicate is in backup slurries and as a backup stucco. A wide variety of grain and flour sizes are available to fit your needs.

Typical Material Properties*

Chemical Analysis (%)	M47		M60		M70		
	Typical	Specifications	Typical	Specifications	Typical	Specifications	
Aluminum Oxide (Al ₂ O ₃)	46.8	46.0 min	58.6	58.0 min	67.7	67.0 min	
Silicon Dioxide (SiO ₂)	50.0		37.8		27.7		
Titanium Dioxide (TiO ₂)	1.89		2.21		2.80		
Ferric Oxide (Fe ₂ O ₃)	0.95	1.0 max	1.13	1.35 max	1.50	1.75 max	
Calcium Oxide (CaO)	0.04		0.06		0.06		
Magnesium Oxide (MgO)	0.08		0.07		0.07		
Sodium Oxide (Na ₂ O)	0.09		0.07		0.07	0.40 max	
Potassium Oxide (K ₂ O)	0.09		0.04		0.05		
Phosphorous Pentoxide (P ₂ O ₅)	0.09		0.10		0.11		

Mineralogy	M47		M60		M70		
	Typical	Specifications	Typical	Specifications	Typical	Specifications	
% Mullite	65		77		87		
% Glass	20		23		13		
% Cristobalite	15		Tr		Tr		

Physical Properties	M47		M60		M70		
	Typical	Specifications	Typical	Specifications	Typical	Specifications	
Bulk Density (ASTM C- 357, gm/cc)	2.58	2.60 min	2.72	2.78 min	2.80	2.75 min	
Apparent Porosity (%)	4.0		3.8		4.0		
PCE	35 (3245°F)		37 (3308°F)		39 (3390°F)		

^{*}These results are based on the testing methods, frequency and procedures of Ransom & Randolph or its approved suppliers. The levels referenced herein are only for general guidance and do not constitute a firm specification.



RANSOM & RANDOLPH

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) www.ransom-randolph.com







ALUMINOSILICATE

Grain Size Specifications (% Retained)

USS Sieve Grade	8 2.36 mm	12 1.70 mm	14 1.40 mm	20 850 μm	30 600 μm	40 425 μm	50 300 μm	70 212 μm	100 150 μm	140 106 μm	200 75 μm	270 53 μm	325 45 µm	PAN**
10 x 18 (1)	0 - 3	10 - 25		60 - 82	0 - 15									0 - 5
14 x 28 (1)		0	1 Max	30 - 55	35 - 45	10 - 25	5 Max							1.5 Max
16 x 30 (1,2)			0 - 3	65 - 75		4 Max								1 Max
22S (1,2)			TR	15 - 25	32 - 47	27 - 37	4 - 10						3 Max	TR
35S (1,2)			TR	1-5	21 - 38	40 - 54		9 - 19		2-8				3 Max
50S (1,2)				0	1-9	22 - 37	26 - 40	12 - 22	6 - 16	1-6				3 Max
60S (1,2)					0	0 - 5	30 - 48	30 - 44	9 - 22	2 - 7				3 Max
20 x 50 (1,2)			TR	0 - 8	20 - 50		50 - 72						2 Max	TR
25 x 80 (1,2)				0 - 5	20 Min 30 Avg	20 Min 30 Avg	80 - 93	7 - 12						3 Max
50 x 100 (1)						TR	5 - 20		70 - 86	0 - 15	3 Max		1 Max	TR
60 x 200 (1)							0	0 - 11		65 - 90	5 - 20	0 - 6		3 Max
200 IC-C (1,2,3)									TR		15 - 25			75 - 85
325 IC-C (1,2,3)									TR				5 - 15	85 - 95

^{**}PAN designates the percentage of material passing the last reported screen for each size. Grade available in Al₂O₃ content (1) 47% (2) 60% (3) 70%.

IMERYS Refractory Minerals has determined test method and provided analysis as noted herein.

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.



RANSOM & RANDOLPH

Issue Date: February 5, 2024